

Application No. 10/528,298
Amendment Dated February 4, 2008
Reply to Office Action Dated November 5, 2007

Amendments to the Claims:

This listing of claims will replace all prior versions and listings of claims in the application:

Listing of Claims:

1 – 10. (cancelled)

11. (previously presented) A process for preparing a modified diisocyanate to which is attached a pendant aliphatic chain containing at least 15 carbon atoms, said process for obtaining said modified diisocyanate comprising the steps of:

reacting an isocyanate functional group of a triisocyanate with a terminal functional group of an aliphatic chain; and

carrying out said preparation of the modified diisocyanate in a solvent medium with stirring and heating.

12. (previously presented) The process for preparing a modified diisocyanate as claimed in claim 11, wherein said terminal functional group is selected from alcohols, anhydrides, carboxylic acids and amines.

13. (previously presented) A process for preparing a self-lubricating insulating varnish having a modified polymer comprising a base polymer to which is attached a pendant aliphatic chain containing at least 15 carbon atoms, said process comprising the following steps:

- preparing a modified diisocyanate as claimed in claim 11; and
- mixing said modified diisocyanate with at least one difunctionalized monomer containing two second functional groups which are reactive with the first isocyanate functional groups of the modified diisocyanate, to carry out said synthesis of said modified polymer.

14. (previously presented) The process for preparing a self-lubricating insulating varnish as claimed in claim 13, wherein said base polymer is a polyamide-imide.

15. (previously presented) The process for preparing a self-lubricating insulating varnish as claimed in claim 13, wherein said base polymer is selected from polyurethanes, polyamides, polyesters, polyester-imides, solderable polyester-imides, polyester amide-imides, polyimides, polyepoxide compounds and polyphenoxide compounds.

16. (currently amended) The process for preparing a self-lubricating insulating varnish as claimed in claim 13, wherein said base polymer is a semiaromatic polyamide and wherein ~~the so-called~~ an anchor group, attaching the base polymer to said pendant aliphatic chain, is a urethane or an amide, such that said self-lubricating insulating varnish is thermally adhering.

17. (previously presented) The process for preparing a self-lubricating insulating varnish as claimed in claim 13, wherein, said base polymer being a polyurethane, the process further comprises a step of mixing the modified polyurethane with a polymer selected from a solderable polyester-imide and a modified solderable polyester-imide.

18. (currently amended) The process for preparing a self-lubricating insulating varnish as claimed in claim 13, wherein a difunctionalized monomer containing two functional groups ~~similar to the isocyanate functional groups of the modified diisocyanate~~ is mixed with said modified diisocyanate.

19. (previously presented) A process for producing an enameled electrical conductor, said process comprising the steps of:

preparing the self-lubricating insulating varnish as claimed in claim 13; and
coating an electrical conductor with a layer of the self-lubricating insulating varnish.